

Trowelable Crack Filler

DESCRIPTION:

AMGUARD® Trowelable Crack Filler is a premium asphalt emulsion based heavy bodied crack filler, which can be easily applied to blacktop pavement defects such as dips, holes and cracks up to 1 1/2" wide. Fills and seals cracks and voids in pavement surfaces, to prevent damaging effects of water penetration and improves overall pavement appearance.

FEATURES:

- Can be used directly from the container
- Adheres tightly to sides of properly prepared cracks and joints to create a waterproof seal
- Helps keep out moisture which reduces pavement break-up caused by freeze/thaw action
- Improves surface appearance by eliminating dirt trapping cracks

CURING TIME:

The surface will usually dry in 4 hours, but weather and thickness may slow drying. Curing to full depth may take 5-7 days. Wait 48 hours before sealcoating over repairs.

PHYSICAL PROPERTIES:

Color - Black
Weight Per Gallon - Approximately 11 lbs.
Solids Content - 75-80%

USES:

To fill and seal cracks up to 1/2 inch wide, in blacktop and concrete surfaces such as walls, driveways, and parking lots. AMGUARD Trowelable Crack Filler may be used to fill voids left by deterioration of the expansion joint material used between concrete slabs.

STORAGE:

Store in a cool, dry area. Avoid freezing. Product is no longer useful after freezing.

PREPARATION:

Clean all dirt, dust and loose materials from cracks with a stiff broom, water stream, and/or compressed air. Dampen the crack. Allow free standing water to dissipate before making application.

CLEAN-UP:

Clean tools with water immediately after use. Filler remaining on tools may be removed with mineral spirits.

INSTRUCTIONS FOR USE:

For best results, apply in dry warm weather. Do not apply when rain is forecasted within 48 hours or when the ambient air temperature is expected to fall below 50°F (10°C).

SERVICE:

Timely service is available within a 300 mile radius of our manufacturing facilities.

APPLICATION:

One gallon fills approximately 12 ft. of 1 1/2" wide x 1" deep cracks. Apply AMGUARD Trowelable Crack Filler with cement trowel or putty knife, by pressing material into crevices to improve bond. Curing time will vary with thickness of application. Do not apply more than 1 1/2" deep in cracks or holes. Do not overfill. If possible, keep traffic off filled areas during curing period or sprinkle sand over filled areas to prevent tracking.

MANUFACTURING & CUSTOMER SERVICE:

BALTIMORE, MD
(866) AMGUARD
Fax (410) 238-3414

CHICAGO, IL
(866) AMGUARD
Fax (847) 678-2652

DETROIT, MI
(866) AMGUARD
Fax (734) 753-9033

MILLBURY, MA
(866) AMGUARD
Fax (508) 791-6339



Corporate Headquarters:
8201 Arrowridge Blvd. Charlotte, NC 28273



Trowelable Crack Filler

CAUTION:

HARMFUL IF SWALLOWED. Contact with any part of the body may cause skin irritation. Wash off with water immediately. Wearing gloves is recommended. KEEP OUT OF REACH OF CHILDREN. KEEP FROM FREEZING. Contains Asphalt CAS #8052-42-4

LIMITED 1 YEAR PRODUCT WARRANTY FROM DATE OF MANUFACTURE: Bonsal American warrants that this product and the materials used therein meet or exceed the applicable standards listed and enforced at the time of manufacture. Bonsal American will replace any product or part which proves defective due to quality of ingredients used or due to the manufacturing process itself. This Warranty shall apply only if the product is used in strict accordance with applicable specifications and instructions provided by Bonsal American for its use, and Bonsal American shall not be liable otherwise. Replacement of any defective product, or, at Bonsal American option, refund of the purchase of any defective product shall be the buyer's sole remedy under this Warranty, and Bonsal American shall in no event be liable for any damages in excess of the purchase price of the defective product. BONSAL AMERICAN SHALL IN NO EVENT BE LIABLE FOR ANY CONSEQUENTIAL, INCIDENTAL, OR SPECIAL DAMAGES.

This Warranty constitutes the sole warranty given by Bonsal American in connection with this product, and Bonsal American has authorized no person to make or give any other warranties or representation, oral or written on its behalf. IN PARTICULAR, THERE ARE NO IMPLIED WARRANTIES, INCLUDING WITHOUT EXCEPTION WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. No modification of this Warranty in favor of any buyer shall be valid unless given in writing and signed by an officer of Bonsal American.

